

Product Information

Typical Properties of Krytox™ General-Purpose Oils and Greases¹

Oil Grades	100	101	102	103	104	105 (H-1)	106	107
GPL Standard Grease Grades	200	201	202	203 (H-1)	204	205 (H-1)	206 (H-1)	207
GPL Extreme Pressure Grease Grades	210	211	212	—	214	215	216	217
GPL Anti-Corrosion Grease Grades	220	221	222	223 (H-1)	224	225 (H-1)	226 (H-1)	227
ISO Grade of Oil ²	5	7	15	32	68	150	220	460
Estimated Useful Range ³								
°C	<-70-66	<-70-104	-63-132	-60-154	-51-179	-36-204	-36-260	-30-288
°F	<-94-150	<-94-220	-81-270	-76-310	-60-355	-33-400	-33-500	-22-550
Oil Viscosity, cSt								
20 °C (68 °F)	12.4	17.4	38	82	177	522	822	1535
40 °C (104 °F)	5.5	7.8	15	30	60	160	243	450
100 °C (212 °F)	—	2	3	5	8.4	18	25	42
204 °C (400 °F)	—	—	—	—	—	3.1	4.1	6
260 °C (500 °F)	—	—	—	—	—	—	2.4	3.3
Oil Viscosity Index	—	—	29	92	111	124	134	145
Oil Pour Point								
°C	<-70	<-70	<-63	-60	-51	-36	-36	-30
°F	<-94	<-94	<-81	-76	-60	-33	-33	-22
Oil Density, g/mL								
0 °C (32 °F)	1.87	1.89	1.91	1.92	1.93	1.94	1.95	1.95
100 °C (212 °F)	1.67	1.70	1.72	1.74	1.75	1.76	1.77	1.78
Maximum Oil Volatility, ASTM D2595								
% in 22 hr								
121 °C (250 °F)	90	75	35	7	3	1	<1	—
204 °C (400 °F)	—	—	—	—	—	7	<3	<1
Oil Separation from Grease, ASTM D6184								
wt loss, % in 30 hr								
99 °C (210 °F)	18	9	7	6	5	5	4	4
204 °C (400 °F)	—	—	—	—	—	—	12	12


¹This table gives typical properties (not specifications) based on historical production performance. Viscosity may vary within ±10%. Chemours does not make any express or implied warranty that these products will continue to have these typical properties.

²Approximate

³Based on pour point and where evaporation is approximately 10%.

H-1 incidental food contact approval has been given to products above that have (H-1) after the product name.

Krytox™ GPL 100–107 oils are clear, colorless, fluorinated synthetic oils that are non-reactive, nonflammable, safe in chemical and oxygen service, and are long-lasting. Krytox™ is a perfluoropolyether (PFPE)—also called perfluoroalkylether (PFAE) or perfluoropolyalkylether (PFPAE)—with the following chemical structure:



The polymer chain is completely saturated and contains only carbon, oxygen, and fluorine. On a weight basis, a typical Krytox™ oil contains 21.6% carbon, 9.4% oxygen, and 69.0% fluorine.

All standard grades of grease are thickened with polytetrafluoroethylene (PTFE), whose formula is $(\text{CF}_2-\text{CF}_2)_n$. This special high efficiency thickener has a melting point of 325 °C (617 °F), and has low molecular weight and sub-micron (0.2 μm) particle size for higher performance in bearings.

Krytox™ GPL 200–207 greases are white buttery greases with all of the same properties as the Krytox™ GPL 100–107 oils that they are made from, but they are in grease form.

Krytox™ GPL 210–217 EP greases are black greases that contain molybdenum disulfide added as an extreme pressure additive for highly loaded gears and bearings.

Krytox™ GPL 220–227 anti-corrosion greases are white greases that contain sodium nitrite. These grades provide rust protection at ambient temperatures, corrosion protection at high temperatures, and anti-wear protection.

The grease additives may alter the chemical resistance of the grease.

The standard grease consistency is NLGI grade 2 penetration (265–295). Softer or harder NLGI penetration grades can be made by special order.

Special non-melting Krytox™ XHT grades are available for applications that are higher than the 325 °C (617 °F) melting point of the standard PTFE thickener.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For product information, industry applications, technical assistance, or global distributor contacts, visit krytox.com or within the U.S. and Canada, call 1-844-773-CHEM/2436 or outside of the U.S., call 1-302-773-1000.

© 2015 The Chemours Company FC, LLC. Krytox™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

Replaces: H-58510-7
C-10296 (9/15)